


Buckeye®

# 1<sup>st</sup> DOWN®

STAIN-RESISTANT SEAL/SPECIALTY COATING



## Available Packaging



## The 1<sup>st</sup> Down Difference

1<sup>st</sup> Down is a semi-permanent undercoating for Buckeye floor finishes that resists stains and detergents, and protects floors from dirt penetration. 1<sup>st</sup> Down is self-leveling and may be applied to virtually any resilient and hard floor surfaces. It may also be used alone as a sealer/top coat combination on non-resilient floors (quarry tile, brick, concrete, terrazzo, etc.).

### Ideal for use on:

#### Resilient floors:

- Vinyl
- Vinyl Composition
- Linoleum
- Asphalt

#### Masonry floors:

- Concrete
- Quarry Tiles
- Stone
- Brick

#### Hard surface floors:

- Terrazzo
- Slate
- Marble
- Travertine

## FEATURES

- Resists stains and detergents — extends strip cycles
- Dries water clear — floors look newer longer
- Versatile — for use on resilient and hard floor surfaces
- Low odor — eliminates exposure to objectionable fumes
- Slip resistant — U.L. listed for slip resistance
- Self-leveling — easy to apply

NOTE: 1<sup>st</sup> Down is not for use on floors subjected to standing water



# 1<sup>st</sup> DOWN<sup>®</sup>

STAIN-RESISTANT SEAL/SPECIALTY COATING

## DIRECTIONS FOR USE

### FLOOR PREPARATION:

1. Strip floor thoroughly using Buckeye **Revelation<sup>®</sup>** or **Juggernaut<sup>®</sup>**.
2. Pick up stripper solution and rinse floor with clean water until no residue remains.
3. Allow floor to dry before coating application.

### APPLICATION:

1. Use a clean synthetic mop and a clean bucket and wringer.
2. Saturate the mop and press firmly into the wringer to remove excess seal. Do not wring the mop.
3. Apply **1<sup>st</sup> Down** using an overlapping figure-eight motion.
4. Allow floor to dry (usually 20 to 30 minutes).
5. When using as a base coat for Buckeye floor finish, two coats are recommended. When using as a specialty coating, apply a minimum of three coats. Always allow floor to dry thoroughly between coats.

### MAINTENANCE:

1. Dust floor with untreated dust mop.
2. Damp mop as required, using **Buckeye Blue All-Purpose Cleaner** or **Straight-Up<sup>®</sup> pH Neutral Cleaner**.
3. Top scrub and recoat as needed.

## TECHNICAL SPECIFICATIONS

Total Solids (105°F)	16.2 ± 0.2
pH	8.2 ± 0.2
Weight/Gallon	8.58 lbs
Leveling	Excellent
Freeze-Thaw Stability	Passes 3 cycles
Drying Time	20-30 Minutes
Flash Point	None
Film Color	Clear



**BUCKEYE INTERNATIONAL, INC.**

2700 WAGNER PLACE • MARYLAND HEIGHTS • MO 63043 • USA • 800.321.2583

[www.buckeyeinternational.com](http://www.buckeyeinternational.com)