

Clarion® 25

HIGH SOLIDS/METAL INTERLOCK FLOOR FINISH



The Clarion 25 Difference

Clarion 25 is a High Solids/Metal Interlock Floor Finish that maintains its high gloss with minimal maintenance. **Clarion 25** is an extremely durable floor finish that is ideal when there is limited equipment or manpower for a buffing program. **Clarion 25** is versatile and may be used on all porous floors.


MICROBAN®

Microban technology is built-in antimicrobial protection that gives **Clarion 25** an added level of protection against damaging microbes such as bacteria, mold and mildew that can cause stains, odors, and product deterioration.

Microban protection also keeps floors cleaner, longer.

All Microban antimicrobial technologies are approved by the US EPA for their specific use in the product in which they are used.

Available Packaging



FEATURES

Easy to Apply

- High gloss
- Self-Leveling — Coats apply easily
- Dries rapidly — Reduces labor costs

Highly Durable

- Non-Powdering — Finish stays intact to last longer
- Non-Yellowing — Extends stripping intervals, reducing labor cost
- Holds up under extreme conditions

Minimal Maintenance

- Detergent resistant — Holds up to repeated moppings
- Resists scuffs — Floors look better longer

Versatile

- Resilient floors — Vinyl, rubber, asphalt, vinyl composition tile
- Hard floors — Terrazzo, slate, marble, concrete, quarry tile
- Ideal for grocery store aisles, school and university halls and classrooms, and more



Clarion[®] 25

HIGH SOLIDS/METAL INTERLOCK FLOOR FINISH

DIRECTIONS FOR USE

FLOOR PREPARATION:

1. Strip floor using Buckeye **RipSaw[®]** or other Buckeye stripper.
2. After picking up solution, rinse floor until no residue remains.
3. Allow floor to dry before applying **Clarion 25**.

APPLICATION:

1. Use a clean mop and bucket.
2. Saturate mop, press firmly into wringer to remove excess finish. Do not wring mop.
3. Apply **Clarion 25** in even coats.
4. Allow each coat to dry, usually 20 to 30 minutes under normal humidity conditions.
5. Apply seven coats to achieve maximum gloss and durability. Apply four coats maximum per 24-hour period.

MAINTENANCE:

1. Dust mop floor.
2. Damp mop as needed, using Buckeye **True 7[™]**.

TECHNICAL SPECIFICATIONS

pH	8.6 ± 0.4
Leveling	Excellent
Freeze/Thaw Stability	Passes 3 cycles
Removability	Excellent
Drying Time	20–30 minutes
Black Mark Resistance	Excellent
Film Color	Water-Clear
Scrubability	Excellent
Weight/Gallon	8.56 lbs
Slip Resistance	U.L. Classified



For more information about Clarion 25, scan this code.



BUCKEYE INTERNATIONAL, INC.

2700 WAGNER PLACE • MARYLAND HEIGHTS • MO 63043 • USA • 800.321.2583

www.buckeyeinternational.com